

<b>Thesis Title</b>	Improvement of Surface Properties of MJ12 and MJ47 Alloys by High Temperature Nitridation Process						
<b>Author</b>	Mr. Kittichai Sopunna						
<b>Degree</b>	Doctor of Philosophy (Materials Science)						
<b>Thesis Advisory Committee</b>	<table> <tr> <td>Assoc. Prof. Dr. Somchai Thongtem</td> <td>Chairperson</td> </tr> <tr> <td>Assoc. Prof. Titipun Thongtem</td> <td>Member</td> </tr> <tr> <td>Dr. Pisith Singjai</td> <td>Member</td> </tr> </table>	Assoc. Prof. Dr. Somchai Thongtem	Chairperson	Assoc. Prof. Titipun Thongtem	Member	Dr. Pisith Singjai	Member
Assoc. Prof. Dr. Somchai Thongtem	Chairperson						
Assoc. Prof. Titipun Thongtem	Member						
Dr. Pisith Singjai	Member						

### Abstract

Two alloys, Ti-47Al-2Nb-2Cr (MJ12) and Ti-47Al-2Nb-2Mn+0.8TiB<sub>2</sub> (MJ47), were nitrided in purified ammonia for 1 - 10 h at a temperature range of 800 – 1,000 °C. The flow rate of the gas was kept constant at 10 cm<sup>3</sup>.s<sup>-1</sup>. After nitridation, the alloys were analyzed using a pin-on-disk wear tester and Knoop hardness (HK) tester. The alloys were analyzed using XRD, SEM, EDX and an optical microscope to determine phases, morphologies and elements. It was found that hardness of MJ12 and MJ47 for 50 gf load with 1,000 °C nitridation for 10 h was the highest at 700.5 ± 9.0 and 694.7 ± 21.8 kg.mm<sup>-2</sup> or 2.0 and 1.6 times of the non-nitride alloys, respectively. But for 10 gf load, hardness of MJ12 and MJ47 was the highest at 835.3±37.5 and 805.0±47.0 kg.mm<sup>-2</sup> or 2.1 and 1.5 times of the non-nitrided alloys, respectively. The nitridation process can successfully improve the alloy hardness which increased with an increase of the nitridation temperature and time. The wear rate and friction coefficient were significantly reduced by the nitridation process. Wear resistance of both alloys was increased by two orders of magnitude after nitridation comparing to the corresponding non-nitrided alloys.

## ชื่อเรื่องวิทยานิพนธ์

การปรับปรุงสมบัติพิวของโลหะผสม เอ็มเจ 12 และ เอ็มเจ 47 โดยกรรมวิธีในไตรเดชันที่อุณหภูมิสูง

ผู้เขียน

นาย กิตติชัย โสดันนา

บริษัทฯ

วิทยาศาสตรคุณวิปันธิต (วัสดุศาสตร์)

คณะกรรมการที่ปรึกษาวิทยานิพนธ์

รศ.ดร. สมชาย ทองเต็ม

ประธานกรรมการ

รศ. นิติพันธุ์ ทองเต็ม

กรรมการ

ดร. พศิษฐ์ สิงห์ใจ

กรรมการ

บทคัดย่อ

ในไตรเดชันของ Ti-47Al-2Nb-2Cr (MJ 12) และ Ti-47Al-2Nb-2Mn+0.8TiB<sub>2</sub> (MJ 47) ได้ถูกศึกษาในแก๊สแอมโมเนีย โดยใช้อัตราการไหลดของแก๊สคงที่ 10 ลูกบาศก์เซนติเมตรต่อวินาที กระบวนการในไตรเดชันได้ทำที่อุณหภูมิ 800-1000 องศาเซลเซียส เป็นเวลา 1-10 ชั่วโมง แล้วจึงนำสารตัวอย่างไปวิเคราะห์ SEM, XRD, EDS, OM, อุปกรณ์วัดค่าความแข็งแบบนูป และอุปกรณ์วัดการสึกหรอแบบ rub-on-disk เพื่อที่จะกันหายาเฟส รูปร่างลักษณะและสารที่เกิดขึ้น ผลการวิเคราะห์พบว่าความแข็งแบบนูปสูงสุดของโลหะผสมเอ็มเจ 12 และเอ็มเจ 47 สำหรับน้ำหนักกด 50 gf อยู่ที่อุณหภูมิ 1,000 องศาเซลเซียส และเวลา 10 ชั่วโมง มีค่าเป็น  $700.5 \pm 9.0$  และ  $694.7 \pm 21.8$  กิโลกรัมต่ำตาร่างมิลลิเมตร หรือเป็น 2.0 และ 1.6 เท่า ของโลหะผสมที่ไม่ได้ผ่านการทำในไตรเดชันตามลำดับ แต่สำหรับ 10 gf ความแข็งแบบนูปสูงสุดก็อยู่ที่อุณหภูมิ 1,000 องศาเซลเซียส และเวลา 10 ชั่วโมง เช่นเดียวกับน้ำหนักกด 50 gf โดยที่มีค่าเป็น  $835.3 \pm 37.5$  กิโลกรัมต่ำตาร่างมิลลิเมตร สำหรับเอ็มเจ 47 หรือเป็น 2.1 และ 1.5 เท่า ของโลหะที่ไม่ได้ผ่านกระบวนการในไตรเดชันตามลำดับ กระบวนการในไตรเดชันสามารถประสนความสำเร็จในการปรับปรุงค่าความแข็งของโลหะผสมโดยที่การเพิ่มขึ้นของค่าความแข็งเพิ่มขึ้นตามอุณหภูมิและเวลาในการทำในไตรเดชัน ค่าอัตราการสึกหรอและสัมประสิทธิ์ของความเสียดทานมีค่าลดลงอยู่ในลำดับที่กำลังสองเท่า ของโลหะผสมที่ไม่ได้ผ่านกระบวนการในไตรเดชัน